

Declaration of Performance SABA MS Floor



Number: 100510/070314

1. Unique identification code: SABA MS Floor
2. Batch number: Printed on packaging
3. Intended use:
 - Sealant for normal or fuel resistant joints in concrete pavements to be used in roads, parking decks, bridge decks, airfields and other trafficked areas.
 - Sealants for pedestrian walkways.
4. Manufacturer: SABA Dinxperlo BV
Industriestraat 3 NL-7091 DC Dinxperlo
The Netherlands, T +31 (0)315 65 89 99
5. Authorized representative: N/A
6. Systems of assessment of performance:
 - System 4
 - System 3
7. Harmonized standard:
 - EN 14188-2, Class A
 - EN 15651-4, Type PW 25LM INT-EXT
8. Notified body: N/A
9. Declared performance

Pre-conditioning: Method B

Substrate: Concrete with SABA Primer 9002

Essential characteristic	Performance	Technical specification
Reaction to fire	Class E	EN 15651-4: 2012
Release of chemicals dangerous to the environment and health	See MSDS	EN 15651-4: 2012
Water tightness and air tightness:		
Volume loss	≤ 10%	EN 14188-2: 2005 & EN 15651-4: 2012
Cohesion for cold climate areas:		
Secant tensile modulus (100%) at -30 °C	NPD	EN 14188-2: 2005 & EN 15651-4: 2012
Tensile properties at maintained extension at -30 °C	NPD	EN 14188-2: 2005 & EN 15651-4: 2012
Durability	Pass	EN 15651-4: 2012
Tensile properties at maintained extension	Pass	EN 15651-4: 2012
Adhesion and cohesion properties at maintained extension after 28 days of immersion in water	Pass	EN 15651-4: 2012
Adhesie/cohesie-eigenschappen onder voorspanning na 28 dagen onderdompeling in zoutwater	Pass	EN 15651-4: 2012
Tear resistance	Pass	EN 15651-4: 2012
Tensile properties (100%)	≥ 0,15 MPa (23 °C) ≤ 0,6 MPa (-20 °C)	EN 14188-2: 2005
Resistance to deformation:		
Elastic recovery	≥ 70%	EN 14188-2: 2005

Cohesion	Pass	EN 14188-2: 2005
Durability of water tightness against liquid chemicals	Pass	EN 14188-2: 2005
Durability of cohesion against liquid chemicals	Pass	EN 14188-2: 2005
Durability of all mandated characteristics against ageing	Pass	EN 14188-2: 2005

The performance of the product identified in points 1 and 2 is in conformity with the declared performance in point 9. This declaration of performance is issued under the sole responsibility of the manufacturer identified in point 4.



SABA Dinxperlo BV
Drs. R.F. de Block, Chief Technology Officer

CE

SABA Dinxperlo BV, Industriestraat 3 NL-7091 DC Dinxperlo
The Netherlands, T +31 (0)315 65 89 99

14

DoP: 100510/070314

SABA MS Floor, EN 14188-2, Class A
&
EN 15651-4, Type PW 25LM INT-EXT

Sealant for normal or fuel resistant joints in concrete pavements to be used in roads, parking decks, bridge decks, airfields and other trafficked areas.

&
Sealants for pedestrian walkways.

Essential characteristic	Performance
Pre-conditioning: Method B	
Substrate: Concrete with SABA Primer 9002	
Reaction to fire	Class E
Release of chemicals dangerous to the environment and health	See MSDS
Water tightness and air tightness:	
Volume loss	≤ 10%
Cohesion for cold climate areas:	
Secant tensile modulus (100%) at -30 °C	NPD
Tensile properties at maintained extension at -30 °C	NPD
Durability	Pass
Tensile properties at maintained extension	Pass
Adhesion and cohesion properties at maintained extension after 28 days of immersion in water	Pass
Adhesie/cohesie-eigenschappen onder voorspanning na 28 dagen onderdompeling in zoutwater	Pass
Tear resistance	Pass
Tensile properties (100%)	≥ 0,15 MPa (23 °C) ≤ 0,6 MPa (-20 °C)
Resistance to deformation:	
Elastic recovery	≥ 70%
Cohesion	Pass
Durability of water tightness against liquid chemicals	Pass

Durability of cohesion against liquid chemicals	Pass
Durability of all mandated characteristics against ageing	Pass

SABA Dinxperlo BV

Industriestraat 3 NL-7091 DC Dinxperlo • PO Box 3 NL-7090 AA Dinxperlo

T +31 (0)315 65 89 99 • F +31 (0)315 65 32 07 • Trade register Arnhem 09065419 • info@saba-adhesives.com • www.saba-adhesives.com

Our recommendations and instructions for use are based on current knowledge and technology. Customers and users must make their own assessment of our products with regard to their desired utilization and requirements. We are not liable if our products are not used according to our recommendations and/or instructions for use. Our general terms and conditions apply to all requests, instructions for use, quotations, orders, and agreements. These general terms and conditions have been filed with the Arnhem Chamber of Commerce under number 09065419 and can also be consulted on our website at www.saba-adhesives.com. At your request, a copy of these terms and conditions will be sent to you free of charge. The general terms and conditions incorporate a limitation of SABA Dinxperlo BV's liability, as well as the choice of Dutch law as the applicable law and choice of the courts of the Netherlands as the forum. Any disputes ensuing from or relating to requests, instructions for use, quotations, orders, and agreements of SABA Dinxperlo BV must be brought before the competent court in the district where SABA Dinxperlo BV is based.

Version number 2018/05/07, this supersedes all previous versions